

PVL8/006 PVultex

PVL8/006 PVultex is a high ammonia prevulcanised natural rubber latex having a low modulus with high purity/low toxicity rating making it an ideal latex for the production of medical goods.

Types of Applications

The major use for PVL/8006 PVultex is in the manufacture of toy balloons where the low modulus offers high and easy inflation.

For coloured balloons, we recommend aqueous pigment dispersions to be used with the latex compound.

Reference can be made to our technical bulletin as a guide for the typical balloon dipping parameters. The technical bulletin is available from our technical department upon request

TYPICAL PROPERTIES			
COLLOIDAL PROPERTIES		PHYSICAL PROPERTIES	
Total Solid Content (%) Mechanical Stability (sec) Ammonia Content (%) Ford Cup 3 Viscosity @ 25 ⁰ C(sec) pH	58.0 1000 min 0.68 30.0 10.8	<u>Unaged</u> Modulus at 700% elongation (MPa) Tensile Strength (MPa) Elongation at Break (%) <u>Aged (22hrs @ 100⁰C)</u> % Retention of : Modulus at 700% elongation Tensile Strength	9.0 28.0 950 50 min 75*

*Average results

HEAD OFFICE : 9/17 MOO 6,THEPKRASATTRI ROAD, RASADA,MUANG, PHUKET 83000, THAILAND TEL : 076 211332, 076-211407 FAX : 076 215966 Tax ID: 0835558007926

FACTORY : 329 MOO 2, THUMYAI, THUNGSONG, NAKORN SRI THAMARAT 80110, THAILAND TEL : 075 773123-4, FAX : 075 773122 www.mmguthrie.com,

All information is given in good faith but without warranty. We will not accept liability for any damage, loss or patent infringement resulting from the use of this information.

mm@ บริษัท เอ็มเอ็มจี โพลีเมอร์ จำกัด Polymer MMG POLYMER COMPANY LIMITED

Recommended Storage Conditions

It is important to store the product under shelter at temperature between 10° C and 38° C. Creaming of latex may still occurs during storage. Therefore it is necessary to mix well the latex before use. As the product is based on natural rubber latex, changes in colloidal properties may occur upon storage. It is recommended to test the colloidal properties of the latex if it is kept in storage over a long period of time.

Handling Precaution

Before handling any type of latices, read product information, Chemical Safety Data Sheets and container labels for safe use, physical and health hazard information.

Type of Packing

Available in both drum and bulk packing.